

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 1 033 433 A2**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
06.09.2000 Bulletin 2000/36

(51) Int. Cl. 7: **D06L 3/02, C11D 3/39,
C11D 7/54, C11D 3/20,
C11D 7/26**

(21) Application number: **99121860.3**

(22) Date of filing: **04.11.1999**

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE**
Designated Extension States:
AL LT LV MK RO SI

(71) Applicant: **Gomes, Jaime Isidoro Naylor Rocha**
4710 Braga (PT)

(72) Inventor: **Lima, Carlos Joaquim Esteves**
Nogueira, 4710 Braga (PT)

(30) Priority: **11.11.1998 PT 10222098**

(54) **Process of protection of dyes on textiles to the attack of bleaching agents such as hydrogen peroxide, perborates and percarbonates**

(57) The invention refers to a process of colour protection of dyed textile goods to the attack by peroxides, either due to industrial bleaching or peroxide application in the washing machine, such as occurs when the textiles are prebleached or washed with detergents that contain peroxides such as perborates and percarbonates. The most sensitive dyes are reactive and sulphur dyes for cotton. Some dyes belonging to these classes lose colour strength and alter their hue.

In this invention a new process of colour protection for dyed goods is revealed, by the application of quenchers, which when applied simultaneously with the peroxide, inhibit the peroxide attack on the dyes present in the textile fibres.

The products claimed in this invention to work as efficient quenchers and colour protectors are ascorbic acid, DABCO or 1,4-diaza-2,2,2-bicyclooctane and diphenylamine.

EP 1 033 433 A2

Description

[0001] Textile cotton and synthetic goods when washed by the consumer are usually washed with detergents containing peroxides, namely perborates and percarbonates. Both these products liberate hydrogen peroxide when in an alkaline medium. The objective is to bleach the fibres every time the clothes are washed, and also to disinfect the textile goods, since the peroxides have an anti-bactericide action.

[0002] The problem is that peroxides also attack some more sensitive synthetic dyes, such as sulphur dyes and some reactive and direct dyes, deteriorating the colour, with loss of colour strength and alteration of hue. Some chromophores which otherwise are not sensitive, in the presence of heavy metal ions, such as Fe^{2+} and Cu^{2+} , deteriorate in the same way as the sensitive chromophores. An example of these are found in whole classes of dyes, otherwise not sensitive, such as disperse dyes for synthetic fibres.

[0003] Usually the attack of peroxides on dyes is through the excited species of singlet oxygen, or through free radicals formed by the decomposition of the peroxide.

[0004] Some products, known as quenchers, are effective in inhibiting the attack of oxygen, in its excited singlet or triplet state, or inhibiting the attack of free radicals.

[0005] The process we claim is through the application of singlet oxygen quenchers, such as DABCO, 1,4-diaza-2,2,2-bicyclooctane, or quenchers of free radicals, such as ascorbic acid and diphenylamine. These products are water-soluble and can be applied mixed with other aqueous products, such as liquid detergents. To be applied with a solid detergent they should be first microencapsulated, since they are either unstable in the presence of oxidants, such as ascorbic acid, or volatile and skin irritant, such as DABCO and diphenylamine. The microcapsule should then release the quencher when the conditions for application are met, immersed in water, rise in temperature or pH. Examples of these polymers are polyvinylpyrrolidone and polyethylene glycol, which are water soluble or urea-formaldehyde type polymers, which are destroyed in alkaline conditions.

[0006] The attack of peroxides on dyes by perborate, percarbonate or hydrogen peroxide, should only occur above 60°C , but in the presence of peroxide activators, such as T.A.E.D., tetraacetylene diamine, it occurs at lower temperatures, down to 40°C or even lower temperatures. The quenchers mentioned also function at these temperatures in the presence of T.A.E.D.

[0007] To evaluate the fastness of the colours to washing with detergents the standard test ISO C06-A2, B2 and C2, which consists in treating the textile sample, together with a blank, with a solution of 4 g/l of standard detergent ECE, 1 g/l of sodium perborate, at 60°C for 30 minutes. Under these conditions we notice some alteration in colour of the most sensitive dyes and some

staining of the blank with the dyes with the most affinity. For evaluation the grey scale can be used, with a classification of 1-5, with the best result at 5 and the worse at 1. If we use the referred quenchers, in solution or microencapsulated, we verify that the colour alteration and the staining are less, usually 1 point higher, which can mean the difference between a pass and a fail. In a practical situation commercial detergents are used and these contain between 15 and 30% of sodium perborate. The number of washes during the life of the textile goods are usually more than one, and as the effect of peroxides is cumulative, colour degradation becomes much more pronounced in subsequent washes to the first wash. The standard test ISO 105 C06-A2, B2, C2, doesn't reflect this situation.

[0008] Another similar situation to bleaching during domestic washing, is that in which peroxides are applied to textile cotton fabrics or knitwear already dyed, with the purpose of saving energy, water or time. In the case of cotton woven fabric the reason for bleaching after dyeing might be to weave yarn in the grey state, before bleaching, since it will have less breakages during the weaving process. In the case of cotton knitwear with reactive dyes, bleaching before dyeing is followed by rinsing, which are water, time and energy consuming processes. Bleaching after dyeing, or post-bleaching, does not need these rinsing stages. The problem in these processes is that if the dyes present in the goods are sensitive to peroxides, such as reactive and sulphur dyes, they would deteriorate and would make these processes not viable.

[0009] If the quenchers already referred are applied simultaneously with the peroxide, the dyes are protected and the post-bleaching can be applied safely.

Example 1

[0010] Sample of 4g of cotton fabric dyed with the dye C.I. Reactive Orange 64, subjected to a washfastness test, in an aqueous solution of 4 g/l of detergent ECE, 1 to 5 g/l of sodium perborate, 1 g/l of sodium carbonate, for 30 minutes at 60°C , to which is added 0,1 to 5% of 1,4-diaza-222-bicyclooctane. The colour of the textile sample doesn't alter under these conditions

Example 2

[0011] A sample of 4g of cotton fabric dyed with the dye C.I. Disperse Blue 56, subjected to a washfastness test, in an aqueous solution of 4 g/l of detergent ECE, 1 to 5 g/l of sodium perborate, 1 g/l of sodium carbonate, for 30 minutes at 60°C , and 0,5 to 10 g/l of copper sulphate, to which is added 0,1 to 5% of 1,4-diaza-222-bicyclooctane. The colour of the textile sample doesn't alter under these conditions.

Example 3

[0012] A sample of 4g of cotton fabric dyed with the dye C.I. Reactive Blue 204, subjected to a washfastness test, in an aqueous solution of 4 g/l of detergent ECE, 1 to 5 g/l of sodium perborate, 1 g/l of sodium carbonate, for 30 minutes at 60°C, to which is added 0,1 to 5% of 1,4-diaza-222-bicyclooctane. The colour of the textile sample doesn't alter under these conditions.

Example 4

[0013] A sample of 4g of cotton fabric dyed with the dye C.I. Solubilised Sulphur Black 1, subjected to a washfastness test, in an aqueous solution of 4 g/l of detergent ECE, 1 to 5 g/l of sodium perborate, 1 g/l of sodium carbonate, for 30 minutes at 60°C, to which is added 0,1 to 5% of ascorbic acid. The colour of the textile sample doesn't alter under these conditions

Example 5

[0014] A sample of 4g of cotton fabric dyed with dye C.I. Reactive Orange 64, subjected to a washfastness test, in an aqueous solution of 4 g/l of detergent ECE, 1 to 5 g/l of sodium perborate, 1 g/l of sodium carbonate, for 30 minutes at 60°C, to which is added 0,1 to 5% of ascorbic acid. The colour of the textile sample doesn't alter under these conditions

Example 6

[0015] A sample of 4g of cotton fabric dyed with the dye C.I. Reactive Orange 64, subjected to a washfastness test, in an aqueous solution of 4 g/l of detergent ECE, 1 to 5 g/l of sodium perborate, 1 g/l of sodium carbonate, for 30 minutes at 60°C, to which is added 0,1 to 5% of diphenylamine. The colour of the textile sample doesn't alter under these conditions

Example 7

[0016] A sample of 4g of cotton fabric dyed with the dye C.I. Reactive Orange 64, subjected to a washfastness test, in an aqueous solution of 4 g/l of detergent ECE, 1 to 5 g/l of sodium perborate, 1 g/l of sodium carbonate, for 30 minutes at 60°C, to which is added 0,1 to 5% of 1,4-diaza-2,2,2-diazabicyclooctano microencapsulated with a melamine-formaldehyde polymer. The colour of the textile sample doesn't alter under these conditions

Example 8

[0017] A sample of cotton fabric, having a design with unbleached and colour yarns, dyed with reactive or sulphur dyes, bleached with hydrogen peroxide, in an alkaline medium, and simultaneously with 0,1 to 5 g/l of

ascorbic acid. The colour of the dyed yarns doesn't change under these conditions.


Example 9

[0018] A sample of knitwear dyed with reactive dyes, bleached with hydrogen peroxide, in an alkaline medium, and simultaneously with 0,1 to 5 g/l of ascorbic acid. The colour of the dyed knitwear doesn't change under these conditions.

Claims

1. Process of treating dyed textile goods, consisting of the application of the product ascorbic acid, for the protection of the dyes present in the textile goods to the attack of peroxides during industrial bleaching with hydrogen peroxide, or its application in domestic washing machines simultaneously with perborates or percarbonates.
2. Process according to claim n° 1, but applying instead the product 1,4-diaza-2,2,2-bicyclooctane, DABCO, for the protection of dyes to peroxides.
3. Process according to claim n° 1, but applying the product diphenylamine for the protection of dyes to peroxides.
4. Process according to claim n° 1, but applying the products referred in claims 1-3, microencapsulated with a polymer, which breaks down when added to the bleaching solution, freeing in so doing the active product.
5. Process according to claim n° 4, in which the polymer is specifically polyvinylpyrrolidone, PVP.
6. Process according to claim n° 4, in which the polymer is specifically a polymer based on derivatives of urea and formaldehyde monomers.
7. Process according to claim n° 4, in which the polymer is specifically polyethyleneglycol.
8. Process according to claim n° 4, in which the polymer is specifically poly-hydroxyethyl-methacrylate, Poly (HEMA)
9. Process according to any of the previous claims, in which the application of the peroxides is done simultaneous with detergent in a washing machine.
10. Process according to claim n° 9, in which the detergent also contains peroxide activators, such as T. A.E.D., tetraacetylenethylenediamine.

This Page Blank (uspto)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 1 033 433 A3**

(12) **EUROPEAN PATENT APPLICATION**

(88) Date of publication A3:
25.10.2000 Bulletin 2000/43

(51) Int Cl.7: **D06L 3/02, C11D 3/39,
C11D 7/54, C11D 3/20,
C11D 7/26**

(43) Date of publication A2:
06.09.2000 Bulletin 2000/36

(21) Application number: **99121860.3**

(22) Date of filing: **04.11.1999**

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE**
Designated Extension States:
AL LT LV MK RO SI

(71) Applicant: **Gomes, Jaime Isidoro Naylor Rocha**
4710 Braga (PT)

(72) Inventor: **Lima, Carlos Joaquim Esteves**
Nogueira, 4710 Braga (PT)

(30) Priority: **11.11.1998 PT 10222098**

(54) **Process of protection of dyes on textiles to the attack of bleaching agents such as hydrogen peroxide, perborates and percarbonates**

(57) The invention refers to a process of colour protection of dyed textile goods to the attack by peroxides, either due to industrial bleaching or peroxide application in the washing machine, such as occurs when the textiles are prebleached or washed with detergents that contain peroxides such as perborates and percarbonates. The most sensitive dyes are reactive and sulphur dyes for cotton. Some dyes belonging to these classes lose colour strength and alter their hue.

In this invention a new process of colour protection for dyed goods is revealed, by the application of quenchers, which when applied simultaneously with the peroxide, inhibit the peroxide attack on the dyes present in the textile fibres.

The products claimed in this invention to work as efficient quenchers and colour protectors are ascorbic acid, DABCO or 1,4-diaza-2,2,2-bicyclooctane and diphenylamine.

EP 1 033 433 A3



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 99 12 1860

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	US 5 622 646 A (PRETTY ALASTAIR J ET AL) 22 April 1997 (1997-04-22) * column 10, line 18 - line 59 * * example II *	1,9,10	D06L3/02 C11D3/39 C11D7/54 C11D3/20 C11D7/26
A	US 5 585 422 A (FALK ROBERT A ET AL) 17 December 1996 (1996-12-17) * column 10, line 21 - line 25 *	1,3	
A	EP 0 436 729 A (KANEBO LTD) 17 July 1991 (1991-07-17) * page 5, line 19 - line 24 * * claims 1-17 *	1,4,6	
A	EP 0 273 775 A (ALBRIGHT & WILSON) 6 July 1988 (1988-07-06) * claims 1-17 *	1-10	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
			D06M D06P C11D D06L C01B
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 4 September 2000	Examiner Richards, M
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03/92 (Pct/C21)

ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.

EP 99 12 1860

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

04-09-2000

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5622646 A	22-04-1997	AT 170553 T	15-09-1998
		CA 2187175 A	19-10-1995
		DE 69504489 D	08-10-1998
		DE 69504489 T	20-05-1999
		EP 0754218 A	22-01-1997
		JP 3009471 B	14-02-2000
		JP 9511774 T	25-11-1997
		WO 9527774 A	19-10-1995
US 5585422 A	17-12-1996	DE 69602902 D	22-07-1999
		DE 69602902 T	11-11-1999
		EP 0764686 A	26-03-1997
		JP 9110841 A	28-04-1997
EP 0436729 A	17-07-1991	WO 9101801 A	21-02-1991
		JP 2562233 B	11-12-1996
		US 5232769 A	03-08-1993
		JP 3163013 A	15-07-1991
EP 0273775 A	06-07-1988	AU 8318487 A	07-07-1988
		BR 8707185 A	09-08-1988
		DK 690187 A	01-07-1988
		FI 875790 A	01-07-1988
		GB 2200377 A	03-08-1988
		JP 1096296 A	14-04-1989
		NO 875493 A	01-07-1988
		PT 86485 A, B	01-01-1988
		ZA 8709757 A	23-06-1988
		CN 1035124 A	30-08-1989
		PT 88721 B	31-12-1992

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

This Page Blank (uspto)